



Technical Data Sheet


ML PROTECT

Cavity protection

PROPERTIES

- A product designed and dedicated for renovation of classic cars
 - Perfect anti-corrosion properties
- Perfect cavity penetrating properties
- Gives an elastic and sealed coating that protects against water and salt



USE	
ML PROTECT is used to protect closed cavities of the body (doors, hood, sills, etc.).	
PROCEDURE	
ML PROTECT is introduced into the closed cavities of the body through special openings at 3 to 6 bar by using a pneumatic gun with a suitable adapter. The product may also be applied with a brush. Remove excess product with white spirit.	
DRYING TIMES	
	2 – 4 h at 20°C
REACTIVITY	
Does not react with paint coatings.	
CONTENT OF VOLATILE ORGANIC COMPOUNDS	
VOC II/B/e limit*	840 g/l
Actual VOC content	395 g/l
* For ready to use mixture acc. to EU Directive 2004/42/CE	
APPLICATION CONDITIONS	
It is recommended to apply the primer at a temperature above 15°C and a humidity of no more than 80 %.	
THEORETICAL YIELD	
1 litre of ML PROTECT gives approx. 7.0 m ² of the dry layer with 50µm of thickness.	
COLOUR	
Brown.	
EQUIPMENT CLEANING	
White spirit or NC solvent.	
STORAGE CONDITIONS	
Store in a cool dry room, away from sources of fire and heat. Avoid direct exposure to sunlight.	
SHELF LIFE	
ML PROTECT	24 months/20°C
SAFETY	
See Safety Data Sheet.	



ML PROTECT

Technical Data Sheet
10/03/2015

OTHER INFORMATIONS

The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a trial/test application of the product due to the potential variation of product performance between substrate materials. We may not be held liable for defects if final results were affected by factors beyond our control.